

Sub
Econcl
D2
concl
D3
Sub
Econcl

layer, comprising an acrylic polymer (a) having a weight average molecular weight of 10000 to 300000 and an acid number of 80 to 250 mgKOH/g and a fluorescent substance (b), and a photosensitive resin composition (B) layer are formed inside the cell, and then they are exposed, developed and baked, wherein the photosensitive resin composition (B) layer is formed in the cell after the resin composition (A) layer is formed.

19. (Amended) A process for forming a pattern of fluorescent substance into the cell of a fluorescent substance display substrate comprising providing inside the cell two separate layers which are (i) a non-photosensitive resin composition (A) layer and (ii) a photosensitive resin composition (B) layer, wherein the resin composition (A) layer, comprising an acrylic polymer (a) having a weight average molecular weight of 10000 to 300000 and an acid number of 80 to 250 mgKOH/g and a fluorescent substance (b), and the photosensitive resin composition (B) layer are formed inside the cell, and then they are exposed, developed and baked, wherein the photosensitive resin composition (B) layer is formed in the cell after the resin composition (A) layer is formed.
